

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 9142 (1979): Specification for Artificial Lightweight Aggregates for Concrete Masonry Units [CED 2: Cement and Concrete]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 9142 - 1979

Indian Standard

SPECIFICATION FOR
ARTIFICIAL LIGHTWEIGHT AGGREGATES
FOR CONCRETE MASONRY UNITS

(First Reprint OCTOBER 1990)

UDC 666.972.125:693.54

© *Copyright* 1979

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

SPECIFICATION FOR ARTIFICIAL LIGHTWEIGHT AGGREGATES FOR CONCRETE MASONRY UNITS

Cement and Concrete Sectional Committee, BDC 2

Chairman

DR H. C. VISVESVARAYA

Representing

Cement Research Institute of India, New Delhi

Members

ADDITIONAL DIRECTOR, STANDARDS (B & S)	STAN- Research, Designs & Standards Organization (Ministry of Railways), Lucknow
DEPUTY DIRECTOR, STANDARDS (B & S) (<i>Alternate</i>)	
SHRI K. C. AGGARWAL	Hindustan Prefab Ltd, New Delhi
SHRI C. L. KASLIWAL (<i>Alternate</i>)	
SHRI K. P. BANERJEE	Larsen & Toubro Ltd, Bombay
SHRI HARISH N. MALANI (<i>Alternate</i>)	
SHRI R. N. BANSAL	Beas Designs Organization, Nangal Township
SHRI T. C. GARG (<i>Alternate</i>)	
DR N. S. BHAL	Structural Engineering Research Centre (CSIR), Roorkee
SHRI R. V. CHALAPATHI RAO	Geological Survey of India, Calcutta
SHRI S. ROY (<i>Alternate</i>)	
CHIEF ENGINEER (DESIGNS)	Central Public Works Department, New Delhi
EXECUTIVE ENGINEER (DESIGNS) III (<i>Alternate</i>)	
CHIEF ENGINEER (PROJECTS)	Irrigation Department, Government of Punjab, Chadigarh
DIRECTOR, IPRI (<i>Alternate</i>)	
DIRECTOR (CSMRS)	Central Water Commission, New Delhi
DEPUTY DIRECTOR (CSMRS) (<i>Alternate</i>)	
SHRI AMITABHA GHOSH	National Test House, Calcutta
SHRI E. K. RAMACHANDRAN (<i>Alternate</i>)	
DR R. K. GHOSH	Central Road Research Institute (CSIR), New Delhi
SHRI Y. R. PHULL (<i>Alternate</i> I)	
SHRI M. DINAKARAN (<i>Alternate</i> II)	
DR R. K. GHOSH	Indian Roads Congress, New Delhi
SHRI B. R. GOVIND	Engineer-in-Chief's Branch, Army Headquarters, New Delhi
SHRI P. C. JAIN (<i>Alternate</i>)	

(Continued on page 2)

© Copyright 1979

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act (XIV of 1957)* and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI A. K. GUPTA	Hyderabad Asbestos Cement Products Ltd, Hyderabad
DR R. R. HATTIANGADI	The Associated Cement Companies Ltd, Bombay
SHRI P. J. JAGUS (<i>Alternate</i>)	Engineering Research Laboratories, Hyderabad
DR IQBAL ALI	Directorate General of Supplies & Disposals, New Delhi
SHRI M. T. KANSE	M. N. Dastur & Co (Pvt) Ltd, Calcutta
SHRI S. R. KULKARNI	The Institution of Engineers (India), Calcutta
SHRI S. K. LAHA	
SHRI B. T. UNWALLA (<i>Alternate</i>)	Central Building Research Institute (CSIR), Roorkee
DR MOHAN RAI	
DR S. S. REHSI (<i>Alternate</i>)	In personal capacity (' Ramanalaya ' 11 First Crescent Park Road, Gandhinagar, Adyar, Madras)
SHRI K. K. NAMBIAR	National Buildings Organization, New Delhi
DR A. V. R. RAO	
SHRI K. S. SRINIVASAN (<i>Alternate</i>)	Gammon India Ltd, Bombay
SHRI T. N. S. RAO	
SHRI S. R. PINHEIRO (<i>Alternate</i>)	Cement Corporation of India Ltd, New Delhi
SHRI ARJUN RIJHSINGHANI	
SHRI K. VITHAL RAO (<i>Alternate</i>)	Central Board of Irrigation and Power, New Delhi
SECRETARY	
DEPUTY SECRETARY (I) (<i>Alternate</i>)	Roads Wing (Ministry of Shipping and Transport)
SHRI N. SEN	
SHRI J. R. K. PRASAD (<i>Alternate</i>)	The India Cements Ltd, Madras
SHRI K. A. SUBRAMANIAM	
SHRI P. S. RAMACHANDRAN (<i>Alternate</i>)	Public Works Department, Government of Tamil Nadu, Madras
SUPERINTENDING ENGINEER (DESIGNS)	
EXECUTIVE ENGINEER (SM & R DIVISION) (<i>Alternate</i>)	
SHRI L. SWAROOP	Dalmia Cement (Bharat) Ltd, New Delhi
SHRI A. V. RAMANA (<i>Alternate</i>)	
SHRI B. T. UNWALLA	The Concrete Association of India, Bombay
SHRI T. M. MENON (<i>Alternate</i>)	
SHRI D. AJITHA SIMHA, Director (Civ Engg)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary

SHRI M. N. NEELAKANDHAN
Assistant Director (Civ Engg), ISI

Concrete Subcommittee, BDC 2 : 2

SHRI C. R. ALIMCHANDANI	Stup Consultants India Ltd, Bombay
SHRI M. C. TANDON (<i>Alternate</i>)	
SHRI D. CHAKRAVARTY	Engineers India Ltd, New Delhi
DEPUTY DIRECTOR, STANDARDS (B & S)	Research, Designs and Standards Organization (Ministry of Railways), Lucknow
ASSISTANT DIRECTOR, STANDARDS (M/C) (<i>Alternate</i>)	

(Continued on page 7)

Indian Standard

SPECIFICATION FOR ARTIFICIAL LIGHTWEIGHT AGGREGATES FOR CONCRETE MASONRY UNITS

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 22 March 1979, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 One of the methods of producing lightweight concrete is by using lightweight aggregates. The essential characteristic of lightweight aggregate is its high porosity which results in a low apparent specific gravity. Some lightweight aggregates occur naturally and others are manufactured. This standard specifies the requirements of artificial lightweight aggregates. The lightweight aggregates covered in this standard are used for manufacture of concrete masonry units (*see* IS : 3590-1966*).

0.2.1 The detailed requirements of cinder aggregates which are also artificial lightweight aggregates used for manufacture of precast blocks, are given in IS : 2686-1977†.

0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960‡. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard covers the requirements of artificial lightweight aggregates, such as foamed blast furnace slag, bloated clay aggregate, sintered fly ash aggregate and cinder aggregate intended for use in concrete masonry units in which prime consideration is lightness in mass.

*Specification for load bearing lightweight concrete blocks.

†Specification for cinder aggregates for use in lime concrete (*first revision*).

‡Rules for rounding off numerical values (*revised*).

2. GENERAL CHARACTERISTICS

2.1 General types of artificial lightweight aggregates covered by this standard are the following:

- a) Aggregates prepared by expanding molten blast furnace slag in limited amount of water or jets of steam, by bloating of clays and shales at high temperature or by sintering of fly ash; and
- b) Cinder aggregates conforming to Class C of IS : 2686-1977*.

2.2 The aggregates shall be composed, predominantly of lightweight cellular and granular inorganic material.

3. GRADING

3.1 The grading of the aggregate, that is, its particle size distribution as obtained by sieve analysis shall be as given in Table 1.

TABLE 1 GRADING REQUIREMENTS FOR LIGHTWEIGHT COMBINED AGGREGATES FOR CONCRETE MASONRY UNITS

Sl. No.	SIZE DESIGNATION	PERCENTAGES (BY MASS) PASSING IS SIEVES						
		20 mm	12.5 mm	10 mm	4.75 mm	2.36 mm	1.18 mm	300 microns
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
i)	Fine aggregate (4.75 to 0 mm)	—	—	100	85-100	—	40-80	10-35
ii)	Coarse aggregate (12.5 to 4.75 mm)	100	90-100	40-80	0-20	0-10	—	—
	(10 to 2.36 mm)	—	100	80-100	5-40	0-20	—	—
iii)	Combined fine and coarse aggregate (10 mm to 0)	—	100	90-100	65-90	35-65	—	10-25

4. BULK DENSITY

4.1 The dry loose bulk density of combined aggregate shall not exceed 1 100 kg/m³.

4.2 **Uniformity of Mass** — The bulk density of successive supplies of lightweight aggregate shall not differ by more than 10 percent from that of the sample submitted for acceptance tests.

*Specification for cinder aggregates for use in lime concrete (first revision).

5. DELETERIOUS SUBSTANCES

5.1 Lightweight aggregates shall not contain excessive amounts of deleterious substances, as determined by the limits described in **5.1.1** to **5.1.3**.

5.1.1 Organic Impurities — Lightweight aggregates, upon being subjected to the test for organic impurities, that produce a colour darker than the standard colour shall be rejected, unless it can be demonstrated that the discolouration is due to small quantities of materials not harmful to the concrete.

5.1.2 Clay Lumps — The amount of clay lumps shall not exceed 2 percent by dry mass.

5.1.3 Loss on Ignition — Loss on ignition of aggregates except cinder aggregates shall not exceed 4 percent by dry mass. For cinder aggregates, loss on ignition shall be as specified in IS : 2686-1977*.

6. CONCRETE MAKING PROPERTIES

6.1 Concrete specimens containing lightweight aggregate under test shall meet the requirements specified in **6.1.1** and **6.1.2**.

6.1.1 Drying Shrinkage — The drying shrinkage of concrete specimens prepared and tested in accordance with **7.7** shall not exceed 0.10 percent.

6.1.2 Sulphate Content — The sulphate content of lightweight aggregate shall not be more than one percent when expressed as sulphuric anhydride (SO_3) by mass.

7. METHODS OF SAMPLING AND TEST FOR AGGREGATE PROPERTIES

7.1 Sampling — The sampling of lightweight aggregates shall be done in accordance with IS : 2430-1969†.

7.2 Grading — Grading of sample of lightweight aggregate shall be done in accordance with the provisions given in IS : 2386 (Part I)-1963‡.

7.3 Bulk Density (Loose) — The aggregate shall be tested in oven-dry conditions according to the requirements given in 3 of IS : 2386 (Part III)-1963§.

*Specification for cinder aggregates for use in lime concrete (*first revision*).

†Methods of sampling of aggregates for concrete.

‡Methods of test for aggregates for concrete: Part I Particle size and shape.

§Methods of test for aggregates for concrete: Part III Specific gravity, density, voids, absorption and bulking.

7.4 Organic Impurities — The aggregate shall be tested in accordance with IS : 2386 (Part II)-1963*.

7.5 Clay Lumps — Clay lumps in aggregate shall be determined as described in IS : 2386 (Part II)-1963*.

7.6 Loss on Ignition — Loss on ignition of the aggregate shall be determined by the method described in 4.2 of IS : 4032-1968†.

7.7 Drying Shrinkage — The drying shrinkage of concrete shall be determined according to the method given in IS : 3590-1966‡.

7.8 Sulphate Content — The sulphate content of sample shall be determined as specified in IS : 4032-1968†.

8. SUPPLIER'S CERTIFICATE AND COST OF TESTS

8.1 The supplier shall satisfy himself that the material complies with the requirements of this standard and, if requested, shall supply a certificate to this effect to the purchaser.

8.2 If the purchaser requires independent tests to be made, the sample for such tests shall be taken before or immediately after delivery, according to the option of the purchaser and the tests carried out in accordance with this standard and on the written instructions of the purchaser.

8.3 The supplier shall supply free of charge the material required for tests.

8.4 The cost of tests carried out under 8.2 shall be borne by:

- a) the supplier, if the results show that the material does not comply with this standard; and
- b) the purchaser, if the results show that the material complies with this standard.

*Methods of test for aggregates for concrete : Part II Estimation of deleterious materials and organic impurities.

†Method of chemical analysis of hydraulic cement.

‡Specification for load bearing lightweight concrete blocks.

(Continued from page 2)

<i>Members</i>	<i>Representing</i>
DIRECTOR	Engineering Research Laboratories, Hyderabad
DIRECTOR (C & MDD)	Central Water Commission, New Delhi
DEPUTY DIRECTOR (C & MDD) (<i>Alternate</i>)	
SHRI V. K. GHANEKAR	Structural Engineering Research Centre (CSIR), Roorkee
SHRI A. S. PRASADA RAO (<i>Alternate</i>)	
DR R. K. GHOSH	Central Road Research Institute (CSIR), New Delhi
SHRI M. R. CHATTERJEE (<i>Alternate</i>)	
SHRI V. K. GUPTA	Engineer-in-Chief's Branch, Army Headquarters, New Delhi
SHRI S. V. TIGARE (<i>Alternate</i>)	
SHRI J. S. HINGORANI	Associated Consulting Services, Bombay
SHRI A. P. REMEDIOS (<i>Alternate</i>)	
SHRI P. J. JAGUS	The Associated Cement Companies Ltd, Bombay
SHRI M. R. VINAYAKA (<i>Alternate</i>)	
SHRI G. C. MATHUR	National Buildings Organization, New Delhi
SHRI G. T. BHIDE (<i>Alternate</i>)	
SHRI K. K. NAMBIAR	In personal capacity (' Ramanalaya ' 11 First Crescent Park Road, Gandhinagar Adyar, Madras)
SHRI N. S. RAMASWAMY	Roads Wing (Ministry of Shipping and Transport)
SHRI R. P. SIKKA (<i>Alternate</i>)	
SHRI T. N. S. RAO	Gammon India Ltd, Bombay
SHRI S. R. PINHEIRO (<i>Alternate</i>)	
SHRI M. P. GAJAPATHY RAO	Public Works and Housing Department, Bombay
SUPERINTENDING ENGINEER, DELHI CENTRAL CIRCLE NO. 2	Central Public Works Department, New Delhi
SHRI S. G. VAIDYA (<i>Alternate</i>)	
DR C. A. TANEJA	Central Building Research Institute (CSIR), Roorkee
SHRI B. S. GUPTA (<i>Alternate</i>)	
SHRI B. T. UNWALLA	The Concrete Association of India, Bombay
SHRI T. M. MENON (<i>Alternate</i>)	
DR H. C. VISVESVARAYA	Cement Research Institute of India, New Delhi
DR A. K. MULLICK (<i>Alternate</i>)	

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha
(Common to all Offices)

Regional Offices:

	Telephone
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	{ 331 01 31 331 13 75
*Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	36 24 99
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 2 18 43 3 16 41 41 24 42
Southern : C. I. T. Campus, MADRAS 600113	{ 41 25 19 41 29 16
†Western : Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093	6 32 92 95

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	{ 2 63 48 2 63 49
‡Peenya Industrial Area 1st Stage, Bangalore Tumkur Road BANGALORE 560058	{ 38 49 55 38 49 56
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	6 67 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
53/5 Ward No. 29, R.G. Barua Road, 5th Byelane, GUWAHATI 781003	3 31 77
5-8-56C L. N. Gupta Marg (Nampally Station Road), HYDERABAD 500001	23 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{ 6 34 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208005	{ 21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
T.C. No. 14/1421, University P.O., Palayam TRIVANDRUM 695035	{ 6 21 04 6 21 17

Inspection Offices (With Sale Point):

Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010	2 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35

*Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, Calcutta 700072

†Sales Office in Bombay is at Novelty Chambers, Grant Road, 89 65 28 Bombay 400007

‡Sales Office in Bangalore is at Unity Building, Narasimharaja Square, 22 36 71 Bangalore 560002

Reprography Unit, BIS, New Delhi, India